


Specification Sheet

Product: Styrene Monomer (SM)

Parameters	Test Method	Result
Purity %	By GLC	Min. 99.5
Relative Density 20°C	ASTM D 1298	0.909 – 0.910
Appearance	Visual	Colorless clear liquid
Colour	Co-Pt	Max. 10
Peroxides ppm	ASTM D 2340	Max. 100
Acetaldehyde as Benzaldehyde %	ASTM D 2119	Max. 0.02
Inhibitor ppm	ASTM D 4590	Max. 15



Note:

The information above is believed to be accurate and represents the best information currently available to us. However, we make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and we assume no liability resulting from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no event shall AGR Enterprises be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damages, howsoever arising, even if AGR Enterprises has been advised of the possibility of such damages.